



TOTAL MATT 2.8

Plastic Paint for indoor and outdoor

pinturas de la peña
fábrica de pinturas

Deep MATT plastic paint, with maximum opacity, excellent washable, perfect finish, no roll marks or shiny patches, no splashes. Great covering power, high washability, whiteness and performance. Specially formulated to minimize imperfections on roof surfaces and walls with indirect lights. It's added with fungicide/alligicidas that inhibit the proliferation of mold and verdin.

Features



Color	Transparent
Finishing	Deep matt (< 3 to 85 ^º) UNE-EN 13300
Specific weight	1,60 +/-0,05 gr./cc.
Viscosity at time of packaging	110 K.U. to 25 °C
Fixed material	64 % +/- 2
Solids in volume %	40 % +/- 2
Performance	8 - 10 m ² /lt by hand, according the adsorption
Resistance to wet abrasion	Clase 2 UNE-EN ISO 11998:2017
Recommended dry thickness	50-60 micron per hand
Drying time to the touch	40 to 60 minutes
Total curing	21 days
Repainted	4 to a 6 hours minimum, maaximum no limit
Thinner	Sweet water
Presentation	4 lt and 14 lt containers
Conservation	Keep the shelter from extreme temperatures.
COV'S	Cat A/a (legal limit 30 g/l) content max < 2 g/l

Application

It can be applied on any building material, plaster, cement, plasterboard, etc. Its application can be brushed, roller or projected to gun.

Surface preparation:

- Before application the surface must be completely clean, dry and free of any contaminants with little adhesion such as dust, grease, waxes or saltpeter.
- Remove paints if they are in poor condition mechanically by scraping or sanding and wash with water to remove the dust generated.
- If the parament has cracks, fill it with mastics suitable to its size and surface.
- Surfaces with possible adhesion problems paint it with an acrylic fixative (Peñafij).

Preparation of the product:

- Add the recommended water according to the chosen application method, mix and homogenize the product before use and occasionally during application.

Distribuidor Oficial de:



Nota: Esta información está basada en el estado actual de nuestros conocimientos, son datos orientativos de carácter general. Describen nuestros productos y orientan al usuario sobre su aplicación y empleo. Debido a la gran variedad de condiciones de uso y soportes no debe tomarse como base de garantía ni objeto de responsabilidad.

www.delapenia.com

Fábrica y oficinas



Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com





TOTAL MATT 2.8

Plastic Paint for indoor and outdoor

Page 2 of 2

pinturas de la peña
fábrica de pinturas

- Use only clean water for dilution.
- Application to brush or roller dilute between 15-20 % first hand and 8-15 % second and successive.
- Gun application with or without air dilute by 20-25%.
- Not to be applied at temperatures below 5°C or above 35°C.

Product formulation

Water, acrylic emulsions, titanium dioxide, calcium carbonates and other charges chosen for this product.

Suitable for household use, not suitable for use in children.

Cautions

- P101 If medical advice is needed, have the container or label on hand.
- P102 Keep out of reach of children.
- P103 Read the label before use.
- P501 Delete the content and/or its container through the selective collection system enabled in your municipality.

EUH208 contains 2-octil-2H-isothiazon-3-one. Mixture of: 5-chloro-2-methyl-2H-isothiazole-3-one [EC No. 247-500-7]; 2-metil.2H-isothiazole-3-one [EC No. 220-239-6] (3:1). It can cause an allergic reaction.

In accordance with R.D. 363/1995 (Directive 67/548/EC) and R.D. 255/2003 (Directive 1999/45/EC), the product is not classified as hazardous. Safety data sheet available to the professional user requesting it.

Distribuidor Oficial de:



Nota: Esta información está basada en el estado actual de nuestros conocimientos, son datos orientativos de carácter general. Describen nuestros productos y orientan al usuario sobre su aplicación y empleo. Debido a la gran variedad de condiciones de uso y soportes no debe tomarse como base de garantía ni objeto de responsabilidad.

www.delapenia.com

Fábrica y oficinas



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas