

SYNTHETIC PRIMER

Antioxidant primer for protection of metal elements

Page 1 of 1

It is a synthetic antioxidant primer aimed at the preparation of iron surfaces for synthetic or cellulosic finishes.



Features	
Color	White, red oxide, green, grey and black
Finish	Matt
Nature	Alkyd-Synthetic
Density	1,5-1,7
Pigment/ Resin ratio	0,87 in volume
Performance	7 - 10 m ² /kg and coat (depending on the surface)
Drying time to touch	15 - 20 minutes
Recoat	8 hours (with cellulosic prducts, wait 24 hours)
Solids in volume	40% in weight
No volatile material	60% in weight
Presentation	Cans of 1, 5 and 20 Kg
Conservation	Keep away from extreme temperatures
Cleaning utensils	Universal solvent

Application

The surfaces painted be prepared to be must in correct and cleaned perfectly. а way for new surfaces it will be necessary to clean, degrease brush and sand and remove dust.

For repainting in those cases where you have to eliminate all or part of the old paint to the metal surface, you will have to use paint removers, make sure that there are no traces of rust and that the remaining paint is in good condition and adhered, and then proceed as if it were a new surface.

Protection of iron and steel surfaces in exteriors and interiors.

Can be used as a preparation for synthetic or cellulose finishes.

Its quick drying makes it useful in the hardware that must be placed immediately.

Precautions: Easily flammable. Protect from sources of ignition. Harmful by inhalation, ingestion and contact with skin. Do not breathe vapors or aerosols.

Method of use

Stir to homogenize the contents of the container. Apply by brush, roller or pistol. Brushing is recommended in difficult areas. To apply to spray gun dilute with 10%-15% solvent for synthetics. We advise two coats to perfectly protect the surface. Clean the tools used with solvent for synthetics.







Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Fábrica y oficinas



Ctra. Orgaz, s/n Apdo. 25 45400 Mora (Toledo) t: +34 925 300409 f: +34 925 341082 e: info@delapenia.com

