

De la Peña

pinturas de la peña
fábrica de pinturas**WATERBORNE SATIN ENAMEL**

Glossy Water Enamel White

Page 1 of 2

Glossy Acrylic Enamel base water of high quality. With great weather resistance, high whiteness, excellent opacity (covered), good flexibility, high hardness and glossy finish; it is easy to use, fast drying, non-yellowing, washable and very low odor. Suitable for the decoration of walls and ceilings; external woodwork (doors, windows, gates, railings), and all kinds of supports of wood, plaster, iron etc. It is formulated and tested for skin pigmentation in painting systems (mix machine) to obtain an infinity of pastel colors. Painting subject to reaction to fire as the laboratory AFITI Euro classification according to **UNE-EN 13501-1 + A1:2010**, having obtained the best possible classification for any **B,s1 - d0**, painting for its zero contribution to the fire and smoke production.

Characteristics

Colour	White
Finishing	Glossy
Specific weight	1,22 gr./cc.
Viscosity on having trippled	95 K.U. to 25 °C
Shine to 60°	> 60 U.B.
Shine to 20°	> 25 U.B.
Fixed material	50 %
Performance	11 - 12 m ² /Lt
Drying time at touch	40 - 60 minutes
Treat	21 days
Repainting	6 - 8 hours
Diluent	Water
Presentation	750 Ml and 4 Lt containers
Conservation	Keep away from extreme temperatures

Application

It can be applied on any building material, plaster, cement, plaster, wood, iron, etc. Your application may be to brush, roller or projected to spray-gun. Before application the facing must be completely clean, dry and free of dust or poorly adherent materials. You do not apply at temperatures below 5°C or higher than 35°C.

Not-Painted Surfaces, or News:

- Building Materials:
Seal the walls with PEÑAFIJ diluted in 4:1 to standardize the application.
In case of efflorescence or saltpeter dealing with solution of diluted acid (SALFUMANT) (except plaster), rinse with plenty of water and dry. Apply a coat of PEÑAFIJ diluted in 4:1.
- Iron and steel surfaces: previously protected with ANTI-CORROSIVE PRIMER.
- Galvanized and aluminum: Apply a first coat of PEÑAIMP.
- Wood and chipboard: Apply a coat of SYNTHETIC SEALER. Softly sand and remove the dust.

Surfaces already painted

- IN GOOD CONDITION:
Softly sand the surface, remove the dust and apply as in new surfaces.
- IN BAD CONDITION:
Remove completely the painting, prepare the surface and apply as if it were a new surface.

Suitable for use domestic, not suitable for children.



Nota: Esta información está basada en el estado actual de nuestros conocimientos, son datos orientativos de carácter general. Describen nuestros productos y orientan al usuario sobre su aplicación y empleo. Debido a la gran variedad de condiciones de uso y soportes no debe tomarse como base de garantía ni objeto de responsabilidad.

Fábrica y oficinas
Ctra. Orgaz, s/n
Apdo. 25 - 45400 Mora (Toledo)
t: +34 925 300 409 f: +34 925 341 082
e: info@delapenia.com



Máster
Internacional
de Empresas



Empresa Certificada en fabricación
y diseño de pinturas al agua.

www.delapenia.com



Trofeo CC100
Compromiso a
la calidad

Delegación
C/Manzanares, 1
13250 Daimiel (Ciudad Real)
t,f: 926 851 102
e: info.daimiel@delapenia.com



pinturas de la peña
fábrica de pinturas

WATERBORNE SATIN ENAMEL

Glossy Water Enamel White

Page 2 of 2

Cautions

S2	Keep out of reach of children
S23/24/25	Do not breathe vapors and avoid contact with eyes and skin.
S51	Use in well ventilated locations.

According to the Royal Decree 363/1995 (Directive 67/548/EC) and the Royal Decree 255/2003 (Directive 1999/45/EC), not this classified as dangerous product. Data sheet security available to the professional user who requests it.



Distribuidor Oficial de:

Nota: Esta información está basada en el estado actual de nuestros conocimientos, son datos orientativos de carácter general. Describen nuestros productos y orientan al usuario sobre su aplicación y empleo. Debido a la gran variedad de condiciones de uso y soportes no debe tomarse como base de garantía ni objeto de responsabilidad.

Fábrica y oficinas
Ctra. Orgaz, s/n
Apdo. 25 - 45400 Mora (Toledo)
t: +34 925 300 409 f: +34 925 341 082
e: info@delapenia.com



Máster
Internacional
de Empresas



Empresa Certificada en fabricación
y diseño de pinturas al agua.

www.delapenia.com



Trofeo CC100
Compromiso a
la calidad

Delegación
C/Manzanas, 1
13250 Daimiel (Ciudad Real)
t, f: 926 851 102
e: info.daimiel@delapenia.com