

# PEÑAMAT

Matte synthetic enamel

Page 1 de 2

Synthetic enamel formulated with a careful selection of resins (alkyd-soy and urea), additives and pigments of high quality, to obtain a product with excellent covering, great hardness, capacity of equalization, filling and leveling Surface. It is suitable for decorating and protecting all types of surfaces (metals, woods, etc.) both indoors and outdoors, as long as it is intended to achieve a highly decorative and durable finish.



#### **Features**

Color	White and black
Finish	Matt smooth
Specific weight	1,03 +/-2 gr/cc.
Viscoity	110 +/-5 sg copa Ford nº4 a 20º C
Matter fixed	56 +/-5 % in weight
Drying time	3-9 hours
Recoat	24 hours minimum
Flash point	90°C
COV'S	Max 275 g/l
Presentation	Cans of 375 ml, 750 ml and 4 lt.

**Applicación** 

Recommended thickness by coat	30-35 micra
Theoretical performance	8 - 12 m <sup>2</sup> /I depending on the surface state
Diluent	Universal, turpentine or turpentine simile
Number of components	1
Ppplication method	Brush, roller, spray gun
Dilution	5 - 10 %

### **Surface preparation**

Apply on a suitable primer or sealant, depending on whether the surface to be protected is metal or wood. Apply two coats of synthetic enamel to the recommended thickness.

#### **Remarks**

Cuando se aplica a pistola el intervalo de repintado mínimo es de 48-72 horas. Cuando el producto se utiliza en exterior la estabilidad de algunos colores amarillos, rojos y naranjas vivos puede ser inferior a la habitual.

### Suitable for use domestic, not suitable for children

#### Safety

The safety instructions on the packaging label must be followed scrupulously, in addition to complying with the requirements of national or local legislation.


As general indications: avoid inhalation of solvent vapors and paint mist, as well as contact of liquid paint with skin and eyes.


If applied in confined spaces, forced ventilation should be provided, accompanied by adequate respiratory protection of the skin and eyes, especially when applied to a pistol.



Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com











# PEÑAMAT

Matte synthetic enamel

Page 2 de 2

Store in dry and isolated places.

There is a safety data sheet available to the professional user who requests it.







Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.





